

# TECHNICAL SPECIFICATIONS

	<b>NATURAL (UNE 56921)</b>	<b>C-08 (UNE 56924)</b>	<b>1+1 (UNE 56926)</b>	<b>M-08 (UNE 56922)</b>	<b>AGLO+2D (UNE 56923)</b>
<b>Length (mm.)</b>	n ± 0.5	n ± 0.5	n ± 0.5	n ± 0.5	n ± 0.5
<b>Diameter (mm.)</b>	n ± 0.4	n ± 0.4	n ± 0.4	n ± 0.3	n ± 0.3
<b>Ovalization (mm.)</b>	< 0.5	< 0.5	-	-	-
<b>Density (kg/m<sup>3</sup>)</b>	125-230	140-250	235-315	260-330	-
<b>Disk Length (mm.)</b>	-	-	≥ 4	-	10-12
<b>Mass (g.)</b>	-	-	-	-	8.4-10
<b>Chamfer Dimension (mm.)</b>	-	-	-	-	4 ± 0.5
<b>Humidity (%)</b>	5-9	5-9	4-8	4.5-8	4-8
<b>Torsion (daN/cm<sup>2</sup>)</b>	-	-	-	-	≥ 7.5
<b>Dust (mg.)</b>	-	≤ 3	≤ 1	-	≤ 1
<b>Capillarity</b>	< 2.5 mm.	< 2.5 mm.	< 1/3 b.	< 1/3 b.	-
<b>Desagglomeration</b>	-	-	absence	absence	absence
<b>Recov. diam. Inst. (%)</b>	≥ 88	≥ 88	≥ 87	≥ 86	-
<b>Recov. diam. 5 min. (%)</b>	≥ 93	≥ 93	≥ 91	≥ 90	-
<b>Extraction Power (daN)</b>	20-40	20-40	20-40	15-40	-
<b>Bacteria (UFC)</b>	< 30	< 30	< 30	< 30	< 30
<b>Mold and yeasts (UFC)</b>	< 10	< 10	< 10	< 10	< 10
<b>Sensory Analysis (UNE 56928)</b>	Abs. Default	Abs. Default	Abs. Default	Abs. Default	Abs. Default
<b>TCA / PCA / TeCA / TBA (ng/L) (UNE 56930)</b>	99% < LQ*	99% < 1.0	99% < LQ*	99% < LQ*	99% < LQ*

< LQ = 0.8 ng/L